

Singapore Standard SS 541 : 2008

**Specification for restraint belts**

**AMENDMENT NO. 1**

April 2012

**1. Page 12, 4.5 Metal components**

*Replace* the last sentence with the following text:

Do the salt-spray test on the load-bearing metal components in accordance with ISO 9227, with an initial exposure of 24 h, followed by 1 h drying and followed by an additional exposure of 24 h. The test is classified as a failure if any corrosion that could affect the function of the components is evident. There shall be no evidence of corrosion of the base metal; tarnishing and /or white scale can be accepted.